

UF3350 TCR™ Resin

June 2007, Revision 6

TCR Composites offers a unique thermosetting epoxy matrix resin system featuring a **6-month shelf life without refrigeration**. This resin is currently used for unitape and fabric, and is available for carbon, glass, aramid, and other fibers. Resin content, resin flow during cure, and tack levels can be tailored to suit your process requirements.

Neat Resin Properties and Applications

Density (g/cc)	Tg (°F/°C) (from G'' DMA curve)	Tensile Modulus (ksi/GPa)	Tensile Strength (ksi/MPa)	Elongation at Break (%)	Tg after 24-Hr Water-Boil (°F/°C)	Water Absorption (%)	Available Fiber Form
1.254	376 / 191	550 / 3.79	6.0 / 41.37	1.2	267 / 131	2.9	Unitape, Fabric

Typical Use

Commercial products, where high temperatures and good hot/wet properties are required.

Cure

There are three recommended cure cycles for UF3350 resin. All three will produce similar properties.

1. $\leq 5^\circ\text{F-per-minute}$ ramp up to 350°F (177°C), hold for 2 hours, $< 5^\circ\text{F-per-minute}$ ramp down to at least 150°F (66°C) before removing from oven.
2. $\leq 5^\circ\text{F-per-minute}$ ramp up to 330°F (166°C), hold for 4 hours, $< 5^\circ\text{F-per-minute}$ ramp down to at least 150°F (66°C) before removing from oven.
3. $\leq 5^\circ\text{F-per-minute}$ ramp up to 310°F (154°C), hold for 8 hours, $< 5^\circ\text{F-per-minute}$ ramp down to at least 150°F (66°C) before removing from oven.

Storage Requirements

The prepregged materials manufactured from this resin shall remain sealed and stored in the original package. The material is to be stored indoors, out of the weather.

The shelf life is 6 months from the date of manufacture when the maximum storage temperature shall not exceed 75°F (24°C).

The shelf life is 3 months from the date of manufacture when the maximum storage temperature shall not exceed 90°F (32°C).

The shelf life is 24 months from the date of manufacture when the maximum storage temperature shall not exceed 0°F (-18°C), with an additional 3 months at $\leq 75^\circ\text{F}$ (24°C)

The values here represent expected ranges based on actual test data. Since the values are specimen-preparation- and test-method-dependent, TCR Composites cannot guarantee that these properties will be obtained in all cases. The data should be used as an indication only, since part or component properties are highly equipment- and process-dependent. It is recommended that end users determine the suitability of this material for each application through their own testing and evaluation. TCR™ is a trademark of TCR Composites, Inc.

TCR Composites 219 North 530 West, Ogden, Utah 84404 USA 1- 800-827-3746 1-801-622-3800

www.tcrcomposites.com