



TR1103 TCR™ Resin

TCR Composites offers a unique thermosetting resin system **that is electrically conductive**, featuring a **one-year shelf life without refrigeration**. This resin is currently used for fabric, and is available for carbon, glass, aramid, and other fibers. Resin content, resin flow during cure, and tack levels can be tailored to suit your process requirements.

Neat Resin Properties and Applications

Density (g/cc)	Tg (°F/°C) (from E'' DMA curve)	Tensile Modulus (ksi/GPa)	Tensile Strength (ksi/MPa)	Elongation at Break (%)	Tg after 24-Hr Water-Boil (°F/°C)	Water Absorption (%)	Available Fiber Form
1.25	250 / 121	374 / 2.58	8.1 / 55.8	2.3	181 / 83	3.9	Fabric

Nominal Electrical Resistance:

- Abraded Surface – **10 KΩ**
- Non-abraded Surface – **50 KΩ**

Typical Use

Commercial and industrial applications where electrical conductivity is necessary. This resin is good for applications where a long shelf life is desired and high-temperature capabilities are not required.

Cure

There are three recommended cure cycles for TR1103 resin. All three will produce similar properties.

1. ≤ 5°F-per-minute ramp up to 310°F (154°C), hold for 1 hour, < 5°F-per-minute ramp down to at least 150°F (66°C) before removing from oven.
2. ≤ 5°F-per-minute ramp up to 290°F (143°C), hold for 2 hours, < 5°F-per-minute ramp down to at least 150°F (66°C) before removing from oven.
3. ≤ 5°F-per-minute ramp up to 270°F (132°C), hold for 3 hours, < 5°F-per-minute ramp down to at least 150°F (66°C) before removing from oven.

Storage Requirements

The prepregged materials manufactured from this resin shall remain sealed and stored in the original package. The material is to be stored indoors, out of the weather.

The shelf life is 12 months from the date of manufacture when the maximum storage temperature shall not exceed 75°F (24°C).

The shelf life is 6 months from the date of manufacture when the maximum storage temperature shall not exceed 90°F (32°C).

The shelf life is 30 months from the date of manufacture when the maximum storage temperature shall not exceed 0°F (-18°C), with an additional 6 months at <75 °F (24°C)

The values here represent expected ranges based on actual test data. Since the values are specimen-preparation- and test-method-dependent, TCR Composites cannot guarantee that these properties will be obtained in all cases. The data should be used as an indication only, since part or component properties are highly equipment- and process-dependent. It is recommended that end users determine the suitability of this material for each application through their own testing and evaluation. TCR™ is a trademark of TCR Composites, Inc.

TCR Composites

219 North 530 West, Ogden, Utah 84404 USA

1-800-827-3746

1-801-622-3800

www.tcrcomposites.com